

### DESCRIPTION

- It is a waterproof mortar made in different colours for grouting ceramic tiles of any type and shape, for exterior and interior use. Grout can be cleaned after it is completely dry
- For filling joints 5 mm to 12 mm wide
- Available in 22 colours

### SUBSTRATE

- The joints must be dry and free from oils, paints and dust
- A protector should be applied when the ceramic tile is absorbent or has an uneven surface
- Ceramic tile surface must be clean before application

### PREPARATION

- Mix the powder with approximately 30% to 34% water
- Never add to the water additive products that we do not recommend
- Do not use water in excess
- Mix to a consistent slurry
- Apply immediately

### APPLICATION

- Spread the slurry with a rubber trowel diagonally across the joints, applying some pressure
- A mortar sprayer can be used
- Application in small areas is recommended
- Do not apply with rain, negative temperatures, direct sunlight and very high temperatures; for more vibrant colours take into consideration possible efflorescences if the environment is very moist or if the substrate is less than 28 days old
- After application, wait for the hardening, approximately 50 to 100 minutes
- Once the grout has started to harden, clean and smooth with a damp sponge if necessary

### CLEANING

- Use an absorbent sponge
- Do not use too much water during cleaning
- Excess powder must be dry-cleaned with a cloth

### COMPOSITION

- White Cement CEM II
- Natural calcium carbonate
- Inorganic additives
- Mineral pigments
- Plasticising resins
- Waterproofing additives

### STORAGE

- Dry and ventilated place, on pallet and in original sealed packages, for one year after the date of packaging

### PRESENTATION

- Cardboard boxes with 6 units of 5 kg (Plastic bag), and packages of 10 kg and 20 kg (Paper bag with inner plastic sheet), mentioning the date of filling

### TECHNICAL DATA

- |                 |                                         |
|-----------------|-----------------------------------------|
| - Period of use | 45 minutes                              |
| - Wetting power | not specified                           |
| - Usage         | see table                               |
| - Dry density   | 1.08                                    |
| - Wet density   | 1.82                                    |
| - Storage       | 12 months after the date of manufacture |

- Our technical information - verbal, written or by testing - is based on our current knowledge and experience, but does not involve any guarantee, so the customer must always test the adaptation of our products to their processes and intended purposes.
- As the application is beyond our control, we do not take any responsibility for any anomalies arising from incorrect use of our products.
- If a poor supply is proven to be our responsibility, it will be limited to the value of the goods used.
- We guarantee the consistency of the quality of our products according to the general conditions of supply.